

Aluminum Level

Order Name: **ALUMINUM**
Test Number: 3800750
Revision Date: 12/12/2022

TEST NAME	METHODOLOGY	LOINC CODE
Aluminum Level	Inductively-Coupled Plasma/Mass Spectrometry	

SPECIMEN REQUIREMENTS

Specimen	Specimen Volume (min)	Specimen Type	Specimen Container	Transport Environment
Preferred	7 mL (0.6)	Serum	Royal Blue - No Additive Clot (Trace Element Free)	Room Temperature
Alternate 1	7 mL (0.6)	Plasma	Royal Blue - EDTA (Trace Element Free)	Room Temperature

Instructions

Specimen Type: Royal blue-top (EDTA) tube OR royal blue-top without EDTA

Specimen Storage: Maintain specimen at room temperature.

Specimen Collection: Separate serum or plasma immediately after the collection, and transfer to a certified metal-free transport tube (PeopleSoft No. 111166) for shipment to the laboratory.

Specimen Stability: Ambient: 14 days, Refrigerated : 14 days, Frozen: 14 days

GENERAL INFORMATION

Expected TAT	2 - 4 days working day.
Performing Labcorp Test Code	071548
Notes	Labcorp Test Code: 071548
CPT Code(s)	82108
Lab Section	Reference Lab